



FIBERCON INTERNATIONAL

100 South Third Street

Evans City, PA 16033

Tel: 724-538-5006 or 1-800-521-9908

Fax: 724-538-9118

Email: info@fiberconfiber.com

Website: www.fiberconfiber.com

MATERIAL DATA SHEET—304 SLIT-SHEET FIBERS

REVISION DATE: 15/03/07
PRODUCT TYPE: Stainless Steel Fibers
MANUFACTURING PROCESS: Slit-Sheet Method
SHAPE: Straight & Deformed

TYPICAL CHEMISTRY & PHYSICAL PROPERTIES:

(Metallurgy is typical, conforming to AISI standards)

% kg	C	Mn	Si	P	S	Cr	Ni	Fe + trace elements
max	0.08	2.0	0.75	0.045	0.03	18—20	8—10,5	balance

Melting Range °F: 2550—2650

Critical Oxidation °F

Cyclic: 1500

Continuous: 1650

Specific Gravity g/cm³: 7.87

Tensile strength MPa (min) @ 20 °C: 515—640 (min) @ 20 °C

TYPICAL DIMENSIONS:

Length	1/2"	3/4"	1"	1 3/8"
Typical Equiv. Ø	0.5	0.50	0.5	0.84
Typical Aspect Ratio (ℓ/Ø)	24	38	50	42
Typical Fiber Count/kg	48,500	32,000	24,000	6,600

These Fibers are manufactured to the requirements of ASTM A820/A820M-06 Type III which specifies the following dimensional tolerances:

Length and Equivalent diameter +/- 10%

Aspect Ratio +/- 15%

Product Information