



FIBERCON INTERNATIONAL

100 South Third Street

Evans City, PA 16033

Tel: 724-538-5006 or 1-800-521-9908

Fax: 724-538-9118

Email: info@fiberconfiber.com

Website: www.fiberconfiber.com

MATERIAL DATA SHEET—430 MELT EXTRACT FIBRES

REVISION DATE: 11/04/07
PRODUCT TYPE: Stainless Steel Fibres
MANUFACTURING PROCESS: Melt-extracted Method
SHAPE: Straight

TYPICAL CHEMISTRY & PHYSICAL PROPERTIES:

(Metallurgy is typical—melt extract is not AISI steel)

% kg	C	Mn	Si	P	S	Cr	Ni	Fe + trace elements
max	0.4	2.0	3.5	0.05	0.05	14—18	-	balance

Melting Range °C: 1482—1530

Critical Oxidation °C

Cyclic: 850

Continuous: 816

Specific Gravity g/cm³: 7.87

Tensile strength MPa (min) @ 20 °C: 865

TYPICAL DIMENSIONS:

Length	19mm	25mm	35mm
Typical Equiv. Ø	0.45	0.50	0.63
Typical Aspect Ratio (ℓ/Ø)	43	50	56
Typical Fibre Count/kg	37,000	26,000	12,000

These Fibres are manufactured to the requirements of ASTM A820/A820M-06 Type III which specifies the following dimensional tolerances:

Length and Equivalent diameter +/- 10%

Aspect Ratio +/- 15%

Product Information