



FIBERCON INTERNATIONAL

100 South Third Street

Evans City, PA 16033

Tel: 724-538-5006 or 1-800-521-9908

Fax: 724-538-9118

Email: info@fiberconfiber.com

Website: www.fiberconfiber.com

MATERIAL DATA SHEET—430 SLIT-SHEET FIBRES

REVISION DATE: 19/03/07
PRODUCT TYPE: Stainless Steel Fibres
MANUFACTURING PROCESS: Slit-Sheet Method
SHAPE: Straight & Deformed

TYPICAL CHEMISTRY & PHYSICAL PROPERTIES:

(Metallurgy is typical, conforming to AISI standards)

% kg	C	Mn	Si	P	S	Cr	Fe
max	0.12	1.00	1.00	0.04	0.03	16—18	balance

Melting Range °C: 1482—1530

Critical Oxidation °C

Cyclic: 870

Continuous: 760—816

Specific Gravity g/cm³: 7.87

Tensile strength MPa (min) @ 20 °C: 483—545 (min) @ 20 °C

TYPICAL DIMENSIONS:

Length	13mm	19mm	25mm	35mm
Typical Equiv. Ø	0.5	0.50	0.5	0.84
Typical Aspect Ratio (ℓ/Ø)	24	38	50	42
Typical Fibre Count/kg	48,500	32,000	24,000	6,600

These Fibres are manufactured to the requirements of ASTM A820/A820M-06 Type III which specifies the following dimensional tolerances:

Length and Equivalent diameter +/- 10%

Aspect Ratio +/- 15%

Product Information